

Public reporting burden for this collection of information is estimated to average 1 hour per response, including the time for reviewing instructions, searching existing data sources, gathering and maintaining the data needed, and completing and reviewing this collection of information. Send comments regarding this burden estimate or any other aspect of this collection of information, including suggestions for reducing this burden to Department of Defense, Washington Headquarters Services, Directorate for Information Operations and Reports (0704-0188), 1215 Jefferson Davis Highway, Suite 1204, Arlington, VA 22202-4302. Respondents should be aware that notwithstanding any other provision of law, no person shall be subject to any penalty for failing to comply with a collection of information if it does not display a currently valid OMB control number. **PLEASE DO NOT RETURN YOUR FORM TO THE ABOVE ADDRESS.**

1. REPORT DATE (DD-MM-YYYY)		2. REPORT TYPE Technical Paper		3. DATES COVERED (From - To) See Attached List	
4. TITLE AND SUBTITLE See Attached List				5a. CONTRACT NUMBER N/A	
				5b. GRANT NUMBER N/A	
				5c. PROGRAM ELEMENT NUMBER N/A	
6. AUTHOR(S) See Attached List				5d. PROJECT NUMBER N/A	
				5e. TASK NUMBER N/A	
				5f. WORK UNIT NUMBER N/A	
7. PERFORMING ORGANIZATION NAME(S) AND ADDRESS(ES) See Attached List				8. PERFORMING ORGANIZATION REPORT NUMBER N/A	
9. SPONSORING / MONITORING AGENCY NAME(S) AND ADDRESS(ES) Kristi Laug AFRL/PROP 1950 Fifth Street Wright-Patterson AFB OH 45433 937-255-3362				10. SPONSOR/MONITOR'S ACRONYM(S) N/A	
				11. SPONSOR/MONITOR'S REPORT NUMBER(S) N/A	
12. DISTRIBUTION / AVAILABILITY STATEMENT Distribution Statement A: Approved for public release; distribution is unlimited.					
13. SUPPLEMENTARY NOTES N/A					
14. ABSTRACT					
15. SUBJECT TERMS					
16. SECURITY CLASSIFICATION OF: UNCLASSIFIED			17. LIMITATION OF ABSTRACT Unlimited Distribution	18. NUMBER OF PAGES See Attached List	19a. NAME OF RESPONSIBLE PERSON Kristi Laug
a. REPORT	b. ABSTRACT	c. THIS PAGE			19b. TELEPHONE NUMBER (include area code) 937-255-3362

Standard Form 298 (Rev. 8-98)
Prescribed by ANSI Std. Z39.18



**Determination of Selected Material
Properties of Castable Thin Film Polyimides
for Applications in
Solar Thermal Propulsion**

By

James Patrick Paxton

**Undergraduate
Senior Year**

**Mechanical and Aerospace Engineering Department
University of Alabama in Huntsville
Huntsville, Alabama**

Presented to

**The AIAA Southeastern Regional Student Conference
April 7 - 8, 1994
Huntsville, Alabama**



This Study Will...

- Provide an Introduction to Typical Applications of Thin Film Polyimides
- Introduce 6FDA + APB Polyimides as an Important Component in Solar Thermal Propulsion
- Show Unique Methods in the Determination of Selected Material Properties of 6FDA + APB Polyimides
- Provide Modulus of Elasticity and Coefficient of Thermal Expansion Data for 6FDA + APB Polyimides



What is a Thin Film?

- Thin Sheet of a Polymer Material
- Typically .0005 - .002 Inches Thick
- Used for Stretched Membrane Mirrors and Parabolic Concentrators
- Examples of Thin Film Materials
 - Mylar™ Polyester Film
 - Kapton™ Polyimide Film
 - 6FDA + APB Polyimide Film




An Application of Thin Film Polyimides

- Solar Thermal Propulsion is Fast Becoming an Attractive Option
for On-orbit Satellite Maneuvers
 - LEO to GEO Orbit
 - High Performance (Typical Isp – 600 - 1000 sec.)
 - Lightweight
- The Components of a Solar Powered Rocket Include...



Typical Solar Thermal Rocket Configuration

SRS Proprietary



SRS Proprietary

940329Ae1409-i3.0c Ae(08) 03-29-94



Benefits of 6FDA + APB Thin Films

- Lightweight
- Optically Transparent
- Stowable / Deployable
- Superior Material Properties
- Wide Temperature Range (-450 – 750°F)
- Castable on Curved Surfaces



Design Parameters for Articles Constructed with Thin Film Polyimides


- External Loads / Pressures
- Environmental Conditions
- Transparency
- Material Properties
 - Modulus of Elasticity
 - Coefficient of Thermal Expansion
 - Coefficient of Moisture Expansion
 - Poisson's Ratio



Theory


- Modulus of Elasticity (Young's Modulus) is given by Hooke's Law

$$\sigma = E\varepsilon \quad (\text{psi})$$



- Coefficient of Thermal Expansion is given by


$$\text{CTE} = \frac{\Delta L}{L \Delta T} \quad (\text{in}/(\text{in}^\circ\text{F}))$$




Thin Film Test Apparatus

- **Conforms to ASTM Standards**
- **Includes Temperature Chamber**
- **Provides Constant Uniform Loading**
- **Incorporates Unique Toggle Grip Design**
- **Computer Data Acquisition System**

Uniaxial Test Apparatus




940328Ae1437b-tiff



940328Ae1437-pm4

940328Ae1437a-tiff

Toggle Grip Design



Computer Test Panel

0

0500

Load / Stress

2500

2000

1500

1000

500

0

-500

Time Dependent Strain

0.25

0.20

0.15

0.10

0.05

0

2.0 min

1.0 min

30 sec

10.0 sec

5.0 sec

2.0 sec

.5 sec

0

Rate

400

450

500

550

600

650

700

750

800

400.0000

Temperature

Start Test

0

Time

Data Rate

0




Experimental Procedure

- **Cast, Cut and Measure Samples**
- **Material Tester Calibration**
- **Perform Modulus Tests on Kapton Polyimide**
- **Perform Modulus Tests on 6FDA + APB Polyimide**
- **Perform CTE Tests on 6FDA + APB Polyimide**
- **Tabulate and Graph Results**
- **Compare Results to Material Source Data**




Modulus of Elasticity Results


.5 mil Kapton Type H Linear Curve Fit




6FDA+APB Polyimide Linear Curve Fit



Comparison of Stress vs. Strain Curves for the 6FDA+APB Polyimide






Modulus of Elasticity Results cont.

	Manufacturer's Data	Harris / NASA	Results of Tests	% Difference
Kapton Type H	430,000 psi 1 mil at 25 °C		467,830 psi .5 mil at 23 °C	8.8 %
6FDA + APB		426,000 psi 452,000 psi	457,500 psi 457,500 psi	7.5 % 1.3 %



Coefficient of Thermal Expansion Results

6FDA+APB Polyimide CTE





Coefficient of Thermal Expansion Results cont.

Average CTE	Harris Data	Results of Tests	% Difference
	27.2E-6 in/(in°F)	25.7E-6 in/(in°F)	5.7%



Conclusions and Recommendations

- All Tests Showed Good Repeatability
- Results Compared Favorably to Source Data
- Values Presented here may be used as Design Parameters for Applications of Thin Films in Solar Thermal Propulsion
- The Determination of other Material Properties is Recommended
- Further Investigation of the Non-linearity in the CTE Curve is Recommended



Acknowledgements

- Phillips Laboratory, Edwards Air Force Base, California
 - Ms. Kristi K. Laug
- SRS Technologies, Huntsville, Alabama
 - Mr. Paul A. Gierow
- NASA LaRC, Langley, Virginia
 - Ms. Anne St. Clair